SATWipes® SAT-C3-7030 Wipe

Saturated nonwoven polyester wipes in center-pull dispenser

Description

The SATWipes C3 consists of a roll of (100) 6"x9" saturated wipes which are dispensed through a center-pull canister. The wipes consist of 100% nonwoven polyester fabric that is hydraulically entangled creating a soft, durable, and clean wipe. The saturation of 70% alcohol and 30% deionized water provides a safe and mild cleaning solution. Refill rolls are available so the dispenser canister may be re-used.

Features and Benefits

- Clean, durable nonwoven wipes
- Consistent solvent application and use
- Up to 35% reduction in solvent use
- Increased safety
- Eliminates solvent bottles
- · Reduces solvent handling
- Convenient and re-usable pop-up dispenser

Applicability

The information presented here is applicable to the part numbers shown below, as well as to any product containing the same materials and produced under the same conditions, regardless of product size or packaging configuration. Please contact a Contec sales representative for more details.

SAT-C3-7030, SAT-C3-7030/18

Technical Data

Wipe material	100% polyester
Wipe construction	Hydro-entangled nonwoven
Solution of saturation; (blend ratio and constituents)	70% isopropanol 30% ultra-pure deionized water

Attribute: (unite)	Value **	Test Method
Attribute; (units)	value	Test Method
Basis weight; (g/m²)	69	
Non-volatile residue, NVR In deionized water; (g/m²) In isopropanol; (g/m²)	0.055 0.008	IEST-RP-CC004.3, Sec. 7.1.2
Specific ions Sodium; (ppm) Chloride; (ppm)	1.9 4.7	
Particles, readily releasable $P \geq 0.5 \mu m; \ (x10^6/m^2)$	16.5	IEST-RP-CC004.2, Sec. 5.1
Fibers > $100\mu m$; $(x10^3/m^2)$	1.0	IEST-RP-CC004.2, Sec. 5.2
Saturation volume tolerance; < 300 mL 300 -1666 mL > 1666 mL	+/- 12% +/- 3% +/- 50 mL	N/A

^{**} ND = None detected; levels are below detection limit of test equipment

Notes:

- 1) Data shown are typical values and should not be used as product specifications.
- 2) Valid product comparisons may only be obtained through side-by-side testing in the same test facility, under similar conditions.
- 3) Current and/or comparison data may be available. Please contact a Contec sales representative for details.

Revision date: 05/25/2011



www.contecinc.com